



VICTOR REINZ™

AFM 30

AFM 30

Technical Data Sheet 330

Edition: 07/2025, supersedes all prior editions.

Please see the latest issue at www.reinz-industrial.com

Material	AFM 30 is an asbestos- free gasket material. It consists of aramide fibers and other asbestos substitutes that are resistant to high temperatures and are processed with high- grade elastomers under elevated pressure and temperature.
Properties	AFM 30 is conformable and exhibits excellent mechanical/ thermal resistance, as shown by its high value of residual stress. It is ideal for sealing gases and fluids.
Application	<ul style="list-style-type: none">• for compressors, pipelines, apparatus, transmissions, gas meters and IC engines• for sealing engine, transmission, hydraulic, and refrigerating oils• for sealing fuels, mixtures of water, antifreeze & corrosion inhibitors• for sealing Freons, alkaline solutions, and solvents
Surfaces	As standard, both sides of AFM 30 are coated with a non- stick, high- friction layer that greatly facilitates disassembly. In most cases, additional surface treatment is unnecessary.
Approvals	<p>DIN- DVGW acc. to DIN 3535, part 6 FA</p> <p>ZP 5123 H₂ tested acc. to certification programme 5123 of DVGW CERT GmbH</p> <p>DIN 30653 (formerly VP 401) Gaskets with higher thermal resistance (HTB)</p> <p>BAM German Federal Institute for Materials Research and Testing, flanged joints in oxygen- conducting steel pipes</p> <p>Germanischer Lloyd (DNV GL) Approval for shipbuilding</p>



VICTOR REINZ™

AFM 30

Technical Data
(nominal thickness
2.00 mm)

Density g/ cm³ 1.75 - 1.95

Ignition loss acc to DIN 52 911 % < 36

Tensile strength

acc. to ASTM F 152 accross grain N/ mm² > 12

acc. to DIN 52 910 accross grain N/ mm² > 9

Residual stress

 acc. to DIN 52 913

16 h, 300 °C N/ mm² ≈ 25

16 h, 175 °C N/ mm² ≈ 36

Compressibility and recovery

acc. to ASTM F 36, procedure J

compressibility % 7 - 15

recovery % > 50

Sealability

 against nitrogen

acc. to DIN 3535, part 6 FA mg/ (s·m) ≈ 0.05

Swelling

 acc. to ASTM F 146

in IRM 903 Oil

 (replaces ASTM Oil No. 3)

5 h, 150 °C

increase in thickness % < 10

increase in weight % < 10

in ASTM Fuel B

5 h, room temp.

increase in thickness % < 10

increase in weight % < 10

in water / antifreeze (50:50)

5 h, 100 °C

increase in thickness % < 5

increase in weight % < 10

Short- term **peak temperature** °C 400

250

Maximum **continuous temperature** °C

Maximum **operating pressure** bar 125



Max. continuous temperature and max. pressure must not occur simultaneously, please refer to the table entitled "Max. operating pressures at various temperatures and with various media".



VICTOR REINZ™

AFM 30

DIN 28091-2:

Cold creep ε_{KSW}	%	7 - 15
Cold recovery ε_{KRW}	%	4 - 8
Hot creep during service $\varepsilon_{WSW/T}$	%	11 - 14
Hot recovery $\varepsilon_{WRW/T}$	%	≈ 0.65
Recovery R	mm	≈ 0.012
Specific leakage rate λ	mg / (s·m)	< 0.1
Residual surface pressure after 1000 h (in air at 100 °C)	%	> 50

Sealing parameters, see corresponding [Table](#)



The data quoted above are valid for the material "as delivered" without any additional treatment. In view of the countless possible installation and operating conditions, definitive conclusions cannot be drawn for all applications regarding the behaviour in a sealed joint. Therefore, we do not give any warranty for technical data, as they do not represent assured characteristics. If you have any doubt, please contact us and specify the exact operating conditions.

Form of delivery

Gaskets according to a drawing, dimensions supplied, or other arrangement.

Sheets 1500 x 1500 mm (standard size)

Nominal thicknesses and tolerances acc. to DIN 28091-1 (mm)

Dimensional limits within a shipment

0.30	±0.10
0.50	±0.10
0.75	±0.10
1.00	±0.10
1.50	±0.15
2.00	±0.20
3.00	±0.30
4.00	±0.40
5.00	±0.50

Max. thickness variation in a sheet:

0.1 mm for sheet thickness ≤ 1.00 mm, and 0.2 mm for thickness > 1.00 mm